

1. TFI ISO/API Casing Products Catalogue

Labels		Outside diameter	Nominal linear mass, T&C	Wall thickness	Type of end-finish					
		D mm	kg/m	t mm	H40	J55 K55	L80 C95	N80 Type 1,Q	C90 T95	P110
1	2	3	4	5	6	7	8	9	10	11
4-1/2	9.5	114.3	14.14	5.21	S	S	—	—	—	—
4-1/2	10.5	114.3	15.63	5.69	—	SB	—	—	—	—
4-1/2	11.6	114.3	17.26	6.35	—	SLB	LB	LB	LB	LB
4-1/2	13.5	114.3	20.09	7.37	—	—	LB	LB	LB	LB
4-1/2	15.1	114.3	22.47	8.56	—	—	—	—	—	LB
5	11.5	127	17.11	5.59	—	S	—	—	—	—
5	13	127	19.35	6.43	—	SLB	—	—	—	—
5	15	127	22.32	7.52	—	SLB	LB	LB	LB	LB
5	18	127	26.79	9.19	—	—	LB	LB	LB	LB
5	21.4	127	31.85	11.1	—	—	LB	LB	LB	LB
5	23.2	127	34.53	12.14	—	—	LB	LB	LB	LB
5	24.1	127	35.86	12.7	—	—	LB	LB	LB	LB
5-1/2	14	139.7	20.83	6.2	S	S	—	—	—	—
5-1/2	15.5	139.7	23.07	6.98	—	SLB	—	—	—	—
5-1/2	17	139.7	25.3	7.72	—	SLB	LB	LB	LB	LB
5-1/2	20	139.7	29.76	9.17	—	—	LB	LB	LB	LB
5-1/2	23	139.7	34.23	10.54	—	—	LB	LB	LB	LB
6-5/8	20	168.28	29.76	7.32	S	SLB	—	—	—	—
6-5/8	24	168.28	35.72	8.94	—	SLB	LB	LB	LB	LB
6-5/8	28	168.28	41.67	10.59	—	—	LB	LB	LB	LB
6-5/8	32	168.28	47.62	12.06	—	—	LB	LB	LB	LB
7	17	177.8	25.3	5.87	S	—	—	—	—	—
7	20	177.8	29.76	6.91	S	S	—	—	—	—
7	23	177.8	34.23	8.05	—	SLB	LB	LB	LB	—
7	26	177.8	38.69	9.19	—	SLB	LB	LB	LB	LB
7	29	177.8	43.16	10.36	—	—	LB	LB	LB	LB
7	32	177.8	47.62	11.51	—	—	LB	LB	LB	LB
7	35	177.8	52.09	12.65	—	—	LB	LB	LB	LB
7	38	177.8	56.55	13.72	—	—	LB	LB	LB	LB
7-5/8	24	193.68	35.72	7.62	S	—	—	—	—	—
7-5/8	26.4	193.68	39.29	8.33	—	SLB	LB	LB	LB	—
7-5/8	29.7	193.68	44.2	9.52	—	—	LB	LB	LB	LB
7-5/8	33.7	193.68	50.15	10.92	—	—	LB	LB	LB	LB
7-5/8	39	193.68	58.04	12.7	—	—	LB	LB	LB	LB
7-5/8	42.8	193.68	63.69	14.27	—	—	LB	LB	LB	LB
7-5/8	45.3	193.68	67.41	15.11	—	—	LB	LB	LB	LB
7-5/8	47.1	193.68	70.09	15.88	—	—	LB	LB	LB	LB
7-5/8	20	168.28	29.76	7.32	S	SLB	—	—	—	—
7-5/8	24	168.28	35.72	8.94	—	SLB	LB	LB	LB	LB
7-5/8	28	168.28	41.67	10.59	—	—	LB	LB	LB	LB
7-5/8	32	168.28	47.62	12.06	—	—	LB	LB	LB	LB
8-5/8	24	219.08	35.72	6.71	—	S	—	—	—	—
8-5/8	28	219.08	41.67	7.72	S	—	—	—	—	—
8-5/8	32	219.08	47.62	8.94	S	SLB	—	—	—	—
8-5/8	36	219.08	53.57	10.16	—	SLB	LB	LB	LB	—
8-5/8	40	219.08	59.53	11.43	—	—	LB	LB	LB	LB
8-5/8	44	219.08	65.48	12.7	—	—	LB	LB	LB	LB
8-5/8	49	219.08	72.92	14.15	—	—	LB	LB	LB	LB
9-5/8	32.3	244.48	48.07	7.92	S	—	—	—	—	—
9-5/8	36	244.48	53.57	8.94	S	SLB	—	—	—	—
9-5/8	40	244.48	59.53	10.03	—	SLB	LB	LB	LB	—
9-5/8	43.5	244.48	64.73	11.05	—	—	LB	LB	LB	LB
9-5/8	47	244.48	69.94	11.99	—	—	LB	LB	LB	LB
9-5/8	53.5	244.48	79.62	13.84	—	—	LB	LB	LB	LB
9-5/8	58.4	244.48	86.91	15.11	—	—	LB	LB	LB	LB
10-3/4	32.75	273.05	48.74	7.09	S	—	—	—	—	—
10-3/4	40.5	273.05	60.27	8.89	S	SB	—	—	—	—
10-3/4	45.5	273.05	67.71	10.16	—	SB	—	—	—	—
10-3/4	51	273.05	75.9	11.43	—	SB	SB	SB	SB	SB
10-3/4	55.5	273.05	82.59	12.57	—	—	SB	SB	SB	SB
10-3/4	60.7	273.05	90.33	13.84	—	—	—	—	SB	SB
10-3/4	65.7	273.05	97.77	15.11	—	—	—	—	SB	SB
11-3/4	42	298.45	62.5	8.46	S	—	—	—	—	—
11-3/4	47	298.45	69.94	9.53	—	SB	—	—	—	—
11-3/4	54	298.45	80.36	11.05	—	SB	—	—	—	—
11-3/4	60	298.45	89.29	12.42	—	SB	SB	SB	SB	SB
13-3/8	48	339.72	71.43	8.38	S	—	—	—	—	—
13-3/8	54.5	339.72	81.1	9.65	—	SB	—	—	—	—
13-3/8	61	339.72	90.78	10.92	—	SB	—	—	—	—
13-3/8	68	339.72	101.19	12.19	—	SB	SB	SB	SB	SB
13-3/8	72	339.72	107.15	13.06	—	—	SB	SB	SB	SB
16	65	406.4	96.73	9.53	S	—	—	—	—	—
16	75	406.4	111.61	11.13	—	SB	—	—	—	—
16	84	406.4	125.01	12.57	—	SB	—	—	—	—
18-5/8	87.5	473.08	130.21	11.05	S	SB	—	—	—	—
20	94	508	139.89	11.13	SL	SLB	—	—	—	—
20	106.5	508	158.49	12.7	—	SLB	—	—	—	—
20	133	508	197.93	16.13	—	SLB	—	—	—	—

S = Short round thread, L = Long round thread, B = Buttress thread